

## FLAT DOT GLOSSY

(ZSO550)

### GENERAL PROPERTIES

- Dot adhesive technology, Permanent adhesive, Glossy surface PVC (Calendared)
- Air Egress, Bubble-free, Easy to install
- Dry application with dot adhesive technology
- Repositionable during installation, but the adhesive is stronger after being positioned.
- Compatible with Eco-solvent, Solvent, Latex and UV curable inks

#### \* Condition / Setting / Caution


Highly recommend to test a sample roll

Recommended for indoor usage

For outdoor use, recommended to use outdoor lamination film to prevent discoloration

Clean a mounting object before applying this film

### Specifications

Length (ft)	164	Width (inch)	54 / 60
Weight (gsm)	280	Coating	Resin
Caliper (mil)	11.0 total (4.0 / 1.0 / 6.0)	Base Material	PVC
		Inks	
Surface	Glossy	Peel Strength (SUS, gf/25mm)	Initial 20 min. ≥ 100
Inner Core (inch)	3		3 days ≥ 450

### KEY FEATURES

- Dot adhesive technology
- Permanent adhesive
- Easy to install (dry application)
- Bubbles free
- White Glossy Finish

### Application

- Architectural window decorations, Glass and Plastic flatness, Window graphics, Labels and decals, Retail aisle banners

### General Information

- Printing Temp : Temperature 15 ~ 30°C (59 ~ 86 °F) / Humidity 30 ~ 60%
- Lamination : Optional
- Storage : Recommended to store in closed original packing in a cool 10 ~ 30°C (50 ~ 77 °F) and dry environment. (Humidity 35 ~ 65% RH)
- Shelf Life : One year, stored in original packing at recommended temperature  
(Coating warranty guaranteed for 6 months from date of purchase)

#### \* Cautions

- Recommended to put blank space on edges when printing
- Recommended to use the products after complete or enough drying time
- Recommended to use double-sided tape or proper finish to prevent detachment from the substrate.

### How to buy :

- Please call 1-470-359-2111 to place an order or visit [www.naturamedia.us](http://www.naturamedia.us) for additional information.
- **ICC Profiles are available** by calling the above number.

*Information provided here is subject to our test criteria and subject to change without prior notice. No media warranty is implied. All material should be tested by purchaser to determine final suitability. Printer and ink change may affect results.*